
http://www.sciencepub.net/list.htm



1 of 1 5/23/2012 9:03 AM

http://www.jofamericanscience.org/

THE JOURNAL OF [an error occurred while processing this directive]



Vol. 6(8), Vol. 6(9), Vol. 6(10), Vol. 6(11), Vol. 6(12)

2011: Vol. 7(1), Vol. 7(2), Vol. 7(3), Vol. 7(4), Vol. 7(5), Vol. 7(6), Vol. 7(7), Vol. 7(1s), Vol. 7(8), Vol. 7(9), Vol. 7(10), Vol. 7(11), Vol. 7(12)

2012: Vol. 8(1), Vol. 8(2), Vol. 8(3), Vol. 8(4), Vol. 8(5), Vol. 8(6), Vol. 8(7), Vol. 8(8), Vol. 8(9), Vol. 8(10), Vol. 8(11), Vol. 8(12)

Subscription: To subscribe to the journal, please contact our editors at editor@americanscience.org or; americansciencej@gmail.com

Marsland Press

PO Box 180432, Richmond Hill, New York 11418, USA

Telephones: 347-321-7172

Email: editor@americanscience.org; americansciencej@gmail.com

Website:http://www.americanscience.org

http://www.americanscience.org/journals

| Terms of Service | Privacy Policy |

© 2005-2012. AmericanScience.org

5/23/2012 8:50 AM 1 of 1

Comparing the behavior of reinforced HSC beams with AFRP bars and confined HSC beams with AFRP sheets under bending

R. Rahgozar ¹, M. Ghalehnovi ², E. Adili ³

University of Shahid Bahonar, Kerman, Iran
University of Sistan and Baluchestan, Zahedan, Iran
Department of Civil Engineering, Islamic Azad University, Zahedan Branch, Zahedan, Iran
ehsan.adili@gmail.com

Abstract: By increasing the use of FRP composites in civil engineering, they seem highly essential to be studied. The purpose of the study is comparison of the behavior of AFRP reinforced HSC beams (reinforced with AFRP bars) and steel reinforced HSC beams which confined with AFRP sheets under bending. Eighteen beams have been modeled with ANSYS. Three beams are HSC which reinforced with AFRP bars. After modeling, the results have been compared with experimental results and then software has been calibrated. Then twelve steel reinforced HSC beams which confined with AFRP sheets (with different number of laminates) have been modeled. In addition three simple steel reinforced HSC beams have been modeled as the base of comparison. At the end behavior of aforementioned beams has been compared and corresponding graphs have been sketched.

[R. Rahgozar, M. Ghalehnovi, E. Adili. Comparing the behavior of reinforced HSC beams with AFRP bars and confined HSC beams with AFRP sheets under bending. Journal of American Science 2011;7(7):271-275]. (ISSN: 1545-1003). http://www.americanscience.org.

Keywords: HSC beams; AFRP bars; bending; modeling; ANSYS

1. Introduction

Fiber-reinforced polymers (FRP) are using in the form of sheets or laminates to confinement and bars to reinforcement the concrete members. In both they have some advantages to steel jackets and steel bars. Steel is an isotropic material and its modulus of elasticity is high, thus the steel jackets stand the great part of axial forces which lead to buckling of steel. On the other hand Poisson ratio of steel is greater then concrete, thus the two materials act separately. Corrosion and hard performance are the other problems of steel jackets (Hoseini et al., 2004). Although using the FRP bars as the main reinforcement isn't common yet, it seems they will play an important role as a main reinforcement soon. Fiber-reinforcement polymers (FRP) in the form of bars or sheets, usually made from one of the three basic types of fibers such as Aramid (AFRP), Carbon (CFRP), and glass (GFRP), represent one of the most promising new developments in the area of structural concrete. High strength, but lightweight fibers encapsulated in a polymer matrix possess noncorrosive, non-conducting, and nonmagnetic purpose structures. The non-corroding characteristics of FRP reinforcement could also significantly increase the service life of ordinary concrete structures (Vatani, 2004, Rashid, 2005). In the case of flexure, the very high strength FRP bars, which exhibit elastic response up to failure, could perhaps be effectively used in combination with high strength concrete (HSC). However the majority of reported research works (Cosenza et al., 1997, Toutanji et al., 2000) dealt only with normal strength concrete (fc 41MPa), while some other (Benmokrane et al., 1996, Masmoudi et al., 1998, Grace et al., 1998) considered concrete with maximum compressive strength (fc) of up to 70 Mpa. Only Theriault and Benmokrane (1998) used concrete with (fc) as high as 100 Mpa. Some other researchers worked on the effect of confinement of RC beams (Dathinh et al., 2004). In this study behavior of HSC beams reinforced and confined with AFRP under bending have been compared. ANSYS 9 has been used for modeling the beams.

2. Modeling with ANSYS

ANSYS is suitable software for nonlinear analysis. Designing with ANSYS has three parts; preprocessor, solution, and postprocessor (Jamshidi et al., 2005). Between more than 100 elements exist in the software, concrete 65; link 8 and solid layer 45 have been used for modeling of concrete, bars or stirrups and sheets respectively (Fig. 1) (Zareinezhad et al.).




Figure 1: Used elements 18 HSC beams all 3 meters length (Fig. 2) have been modeled.




Figure 2: Modeled beams

Three beams are in first group AF2, AF3, and AF4. In these beams tensile bars are AFRP bars but compressive ones are steel because compressive strength of AFRP is less than 20% of its tensile strength. The number in the names determines the number of tensile bars. As supplied by manufacturer the tensile strength and the modulus of elasticity of AFRP bars are 1760 Mpa and 53 Gpa, respectively. Second group has three beams too; ST2, ST3, and ST4. They have steel tensile bars and the number in the names determines the number of tensile bars. This group is the base group and the other groups' beams have been compared with these beams. Tensile strength and modulus of elasticity of steel are 533 Mpa and 2.1×105 Mpa respectively.

The last group has twelve beams which have steel tensile bars and AFRP sheet(s) attached at the bottom of the beams. The tensile strength and modulus of elasticity of AFRP sheets are 2900 Mpa and 120 Gpa respectively. The third group name is SmCn. S and C imply Steel and Confine and m and n are two numbers that determine number of tensile bars and number of AFRP sheet layers respectively. All layers of AFRP have 0.3 mm thickness. All the compressive bars are steel. 26 steel stirrups have been distributed monotonously along the beams. Compressive strength of concrete (f'c) has been considered 84.5 Mpa in all beams. More details are shown in Figure 2. Before modeling of main beams, two experimental results of beams compared with ANSYS results. It can help to check the software. AF-control beam is a

represent of first group. It has AFRP bars as tensile bars and its experimental results have been shown by Rashid et al. (2005) (DF3T1).

Figure 3 compares the results of experimental and modeling beams. After the formation of great cracks, the software couldn't converge the equations and couldn't continue up to complete failure.




Figure 3: AF control beam

STC-control beam is a represent of third group. It has steel tensile bars and a layer of FRP attached at the bottom. Its experimental results have been shown by Sadr Momtazi et al. (2006) (G1). Figure 4 compares the results of experimental and modeling beams.




Figure 4: STC control beam

3. Comparing the behavior of beams

HSC beams which reinforced with AFRP exhibit elastic response up to failure. Figure 5 compares the response of AF2, AF3, and AF4 (First group).




Figure 5: First group beams

HSC beams which reinforced with STEEL exhibit nonlinear behavior after yielding. Figure 6 compares the response of ST2, ST3, and ST4 (second group).




Figure 6: Second group beams

Comparing the behavior of third group beams is shown in figures 7, 8, 9, 10 which show third beams with one, two, three and four AFRP covering layers respectively.




Figure 7: Third group with one layer




Figure 8: Third group with two layers




Figure 9: Third group with three layers




Figure 10: Third group with four layers Figure 11, 12 and 13 show the comparing of beams with 2, 3 and 4 tensile bars respectively.




Figure 11: Beams with two tensile bars




Figure 12: Beams with three tensile bars




Figure 13: Beams with four tensile bars

4. Conclusions

- T1. Beams reinforced with AFRP bars (first group) have linear behavior up to failure. Their fracture is in brittle manner that can be a disadvantage but They have large deflection before failure which can be a caution.
- 2. maximum deflection in HSC beams covered or reinforced with AFRP is higher than HSC beams reinforced with steel bars. Furthermore increase the number of bars. Furthermore increasing the number of tensile bars increases the Maximum deflection tensile bars increases the Maximum deflection of AFRP reinforced and covered beams (first and third groups) but decreases it in steel reinforced beams second group).
- 3. Failure force of AFRP reinforced and covered HSC beams are much higher than steel reinforced. Effect of tensile bars increasing on failure force in AFRP reinforced HSC beams is higher than AFRP covered and steel reinforced ones, furthermore it would be increased by increasing the number of tensile bars in first group and be decreased by increasing the number of bars in second and third groups.
- 4. Failure force in AFRP reinforced HSC beams is less than even one layer AFRP covered HSC beams.
- 5. Failure forces in third group are higher than first group and in all cases their maximum deflections are less than first group. Furthermore in third group effect of tensile bars increasing on failure force is less than the other groups. The mentioned effect become less and less when the number of AFRP layers increased because higher amounts of load are bearing by AFRP covers and number of tensile bars has less effect.
- 6. HSC beams with AFRP covers (third group) have higher ductility than uncovered beams (second group). Ductility factor (μ) increases by increasing the number of AFRP covers.

Acknowledgements:

The writers would like to acknowledge the supports provided by Islamic Azad University of Zahedan. The writers are also grateful to M.J. Mehr Mashhadi and Ar. Gharagozlue for their helping to prepare the softwares.

Corresponding Author:

E. Adili

Department of Civil Engineering Islamic Azad University, Zahedan Branch Zahedan, Iran

E-mail: ehsan.adili@gmail.com

References

- 1. Hoseini, A., Fadayi, S. (2004). "Stress-Strain equations of FRP confined Concrete." First conference of application of FRP composits in structures, I. R. Iran.
- 2. Vatani-Oskooi, A. (2004). "Effect of FRP on reparation of Concrete joints damaged by earthquake." First conference of application of FRP composites in structures, I. R. Iran.
- 3. Bilal, S. et al. (2005). "Effect of fiber reinforced polymer confinement on bond strength of reinforcement in beam anchorage specimens." Journal of Composites for Construction, January / February.
- 4. Dat-Duthinh, Monica Starnes. (2004). "Strength and ductility of concrete beams reinforced with carbon fiber reinforced polymer plates and steel." Journal of Composites for Construction, January / February 2004.
- 5. Cosenza, et al. (1997). "flexural behavior of concrete beams reinforced with fiber reinforced

- plastic (FRP) bars." Proc. 3rd int. RILEM Symp. On Non Metallic (FRP) Reinforcement for Concrete structures, Bagneux, France. 1997.
- 6. Masmoudi, et al. (1998). "Flexural behavior of Concrete beams reinforced with deformed fiber reinforced plastic reinforcing rods." ACI Struct. J, 95 (6), 665-676.
- 7. Rashid, M.A. et al. (2005). "Behavior of Aramid fiber reinforced polymer reinforced high strength concrete beams under bending." Journal of Composites for Construction. March / April 2005.
- 8. Jamshidi, N., Javanbakht, B. (2005). "learning the elements design and strength of materials by ANSYS." Afarang publication.
- 9. Zareinezhad, M., Gorjinezhad, S. "Finite elements analysis and ANSYS." Aras Rayane Publication.
- 10. Sadr-Momtazi, A. et al. (2006). "Behavior of concrete beams reinforced with CFRP and GFRP under bending." 3rd National Congress of Civil Engineering, I. R. Iran.
- 11. Toutanji, H.A., Saafi, M. "flexural behavior of concrete beams reinforced with glass fiber reinforced polymer (GFRP) bars." ACI struct. J., 97(5) 712-719.
- 12. Benmokrane, B. et al. "flexural response of concrete beams reinforced with FRP reinforced bars." ACI struct. J., 93 (1) 46-55.
- 13. Grace, N.F. et al. (1998). "Behavior and ductility of simple and continuous FRP reinforced beams." J. Compos. Constr., 2 (4) 186-194.
- 14. The riault. M., Benmokrane, B. (1998). "Effects of FRP reinforcement ratio and concrete strength on flexural behavior of concrete beams." J. Compos. Constr., 2(1) 7-16.

3/5/2011